



Huizhou Markyn New Energy Co., Ltd.

PRODUCT SPECIFICATIONS

Product	Lithium manganese dioxide battery				
Model Number	CR33600				
Outer Dimension	Φ33.7*61.3				
Drafted	Xueying Li	Checked	Huierer Chen	Approved	Jingxian Chen
2020- 7 -22	2020- 7 -22		2020- 7 -22		

HUIZHOU MARKYN NEW ENERGY CO.,LTD.

<http://www.gmbattery.com>

Email:info@gmbattery.com www.gmbattery.com



CR33600specification	
File No: GMB-SM-CR33600-001	Effective Date: 2020-7-22
Version: A/1	Page: 2 / 11

Catalogue

1 . Application Scope	3
2 . Standard Parameters	3
3 . Performance Standard	4
3.1 Appearance	4
3.2 Standard testing conditions	4
3.3 Leakage Resistance	4
3.4 Discharge Curve	4
3.5 Safety Performance	5
3.6 Mechanical Safety Performance	6
4 . Precautions for used	7
5 . Important Notes	8
6 . Battery Dimension	9
7 . Battery Packing	10
8 . History of Revision	11



CR33600specification	
File No: GMB-SM-CR33600-001	Effective Date: 2020-7-22
Version: A/1	Page: 4 / 11

1 Application Scope

The specification describes standard parameters, electrical characteristics, safety performance, environmental adaptability, test and judgment, operation instructions and safety regulations of the battery.

2 Standard Parameters

No.	Item	Parameter	Notes
1	Capacity	14.7Ah	At 20mA, 2.0V cut-of, 25 °C
2	Discharge current	3A	
3	Cut-off voltage	2.0V	
4	Open-circuit voltage	3.00~3.40	
5	Max. continuous discharge	3 A	
6	Max. pulse current	5A	
7	-20°C discharge (20mA/2.0V)	>3Ah	
8	Operating Temperature	-40°C ~ 85°C	
9	Storage Temperature	-20°C ~ 30°C	
10	Weight	125g	
11	Dimension(dia *height)	Φ33.7*61.3 mm	
12	Shelf life	10 years	



CR33600 specification	
File No: GMB-SM-CR33600-001	Effective Date: 2020-7-22
Version: A/1	Page: 5 / 11

3 Performance Standard

* Appearance

The surfaces of the batteries are clean. There should not be deformation、rust、stain or leakage.

3.1 Standard testing conditions


Unless otherwise specified elsewhere, tests should be conducted at Temperature : 25±5℃ Humidity : 45 ~ 75% barometric pressure : 86 ~ 106kpa

3.2 Leakage Resistance

After 24 hours at 70 °C, the battery was placed at room temperature for 8 hours for visual inspection. There was no leakage, explosion and fire.

3.3 Discharge Curve

容量、电流、温度关系特性






CR33600 specification	
File No: GMB-SM-CR33600-001	Effective Date: 2020-7-22
Version: A/1	Page: 6 / 11


常温负载特性

Load Characteristics at room temp.



温度特性

Temperature Characteristics





CR33600 specification

File No: GMB-SM-CR33600-001

Effective Date: 2020-7-22

Version: A/1

Page: 7/ 11

* Safety Performance

Item	Test method	Standard
External short-circuit (55°C)	After the shell temperature of the tested battery is stable at 55 °C , conduct external short circuit to the battery at this temperature, and the total resistance of the external circuit shall be less than 0.1 Ω. The short circuit shall be continued for at least 1 h after the temperature of the battery shell falls back to 55 °C. Continue to observe the samples for 6 hours.	No explosion No fire
Free Fall	the battery without being discharged falls on the concrete surface from a height of 1 m, each battery shall be dropped 6 times, twice in X, y and Z axes, and then the tested battery shall be placed for 1 h.	No leakage No explosion No fire
high temperature	Put the test battery in the oven, raise the temperature to 130 °C at the speed of 5 °C / min, and keep at this temperature for 10 min	No leakage No explosion No fire
“3 + 1” Reverse charge (single battery)	The tested battery is connected in series with three non discharged batteries of the same model containing a single battery, and the tested battery is connected in reverse with other batteries. The resistance of the circuit shall not be more than 0.1 Ω. Turn on the circuit for 24 hours ,or until the temperature of the battery shell returns to the ambient temperature.	No leakage No explosion No fire
Heat shock	The tested battery was placed at 75 °C for at least 6 hours, and then at - 40 °C for at least 6 hours. The conversion time	No leakage No explosion No fire



CR33600 specification	
File No: GMB-SM-CR33600-001	Effective Date: 2020-7-22
Version: A/1	Page: 8/ 11

	<p>of different temperatures should not exceed 30 min. After 10 cycles, each battery was placed at ambient temperature for at least 24 h.</p>	
--	---	--

* Mechanical safety performance

Item	Test method	Standard
Vibrati on test	<p>The tested battery shall be firmly fixed on the vibration platform of the vibration equipment in such a way that the vibration can be truly transmitted without deformation of the battery. The vibration amplitude of sine wave was 0.8mm. In three mutually perpendicular fixed directions, 12 cycles were carried out in each direction, and the cycle time of each azimuth was 3 h. One of the orientations should be perpendicular to the end face of the battery.</p>	<p>No leakage No explosion No fire</p>
Crush Test	<p>The long axis of the tested battery is squeezed between the two planes by applying pressure through a vise or a hydraulic cylinder with a cylindrical piston. From the initial contact point, the extrusion is carried out continuously at a speed of about 1.5 cm / s until the extrusion force reaches about 13 kn and the pressure is released immediately. The pressure can be applied through a hydraulic cylinder with a piston diameter of 32 mm until the pressure reaches 17 MPa</p>	<p>No leakage No explosion No fire</p>



CR33600 specification	
File No: GMB-SM-CR33600-001	Effective Date: 2020-7-22
Version: A/1	Page: 9 / 11

	cell or cell battery is extruded only once. Observe the battery for at least 6 h.					
Shock test	The tested battery is fixed on the testing equipment with a rigid support which can support all fixed surfaces of the tested battery. Each battery is subjected to three times of impact in three mutually perpendicular fixed directions, a total of 18 times.					No leakage No explosion No fire
	Impact parameters					
	Battery	waveform	peak accelerati	pulss	Number of impacts per axle	
Small	half-sine wave	150g	6ms	3		

4. Precautions for Used

The battery has an explosion resistant construction. But the following cautions should be taken, because combustible materials such as lithium metal and organic electrolyte are contained in the battery.

- * Do not use except inapplicable model or equipment
- * Do not connect more than three cells in series
- * Do not mix different types (chemistries) of batteries
- * Do not short circuit .
- * Do not dispose in fire
- * Do not charge.
- * Do not disassemble
- * Do not connect the wrong polarity (+,-)

5. Important Notes (Warranty)



CR33600 specification	
File No: GMB-SM-CR33600-001	Effective Date: 2020-7-22
Version: A/1	Page: 10 / 11

- 5.1 Warnin Fire and burn hazard. Do not recharge、 short circuit、 over discharge、 crush、 disassemble, heat above 100°C (212°F) or incinerate. Keep battery far away from children put them in original package until ready to use. Dispose of used batteries promptly.
- 5.2 When customer does any work on the battery ignoring instructions in this specification, for example wire is soldered to the tab or battery surface directly; Jiangmen Hongli Energy, Co Ltd. cannot warrant any battery performance including safety and the customer should undertake the responsibility of all damage caused by this battery
- 5.3 Do not solder the battery directly. Excessive heating may cause deformation of the battery components such as the gasket, which may lead to the battery swelling, leakage, explosion or ignition. High temperature and long time may cause heat gathered.
- 5.4 Observe the soldering condition for the tabbed battery to be specified by the manufacturer. Choose the tabbed battery if soldering is required. Excessive heating may cause deformation of the gasket, leakage or performance deterioration of the battery
- 5.5 Tabs can be soldered on the battery terminals directly by spot-welding. The parameters of the spot-welder must be adjusted carefully to avoid the battery being perforated, changing voltage and temperature rising above 65 °C Assure not to exceed the battery temperature higher than 60°C at soldering.
- 5.6 Battery characteristics vary with type and grade, even when batteries are the same size and shape. When replacing batteries with new ones, be sure to carefully check the symbols and numbers on each battery.
- 5.7 Please design equipment so that infants cannot easily remove batteries and swallow them.

6. The Battery Dimensions



CR33600 specification

File No: GMB-SM-CR33600-001

Effective Date: 2020-7-22

Version: A/1

Page: 11 / 11

